



Hi-Temp MSL Grease

- *Features unique MSL additive for outstanding performance.*
- *Resists temperatures in excess of 700°C (1292°F).*
- *Quality formulated with synthetic non-ash base carrier.*

TRUST *Save Money*
OMEGA *Enhance Performance*
TO *Extend Service Life*



TW
PERFORMANCE
POLYMERS & FLUIDS®

SPECIAL FEATURES

Omega 35 Hi-Temp MSL Grease continues to lubricate and protect your expensive equipment long after ordinary greases have "burned" off.

- **Omega 35** features Omega's super fine MSL (Megalite Solid Lubricant) additive to ensure outstanding and reliable performance.
- **Omega 35** takes on temperatures in excess of 700°C (1292°F).
- **Omega 35** is quality formulated with synthetic non-ash forming carriers.

OUTSTANDING PROPERTIES

Omega 35 is the high-temperature MSL grease that:

- Lubricates and protects parts subjected to up to searing heat temperatures.
- Will not burn off to form abrasive ash or carbon residues.
- Has super penetration power and "self-spreads" over applied surfaces.
- Provides many advantages over ordinary high-temperature solid lubricants.

USE FOR

Omega 35 is quality engineered as a general-purpose grease for virtually every type of application where extreme high heat is unavoidable.

Use **Omega 35** in:

- Oven Cars • Brick Kiln Cars • Steel Mills • Baking and Cooking Ovens • Foundries • All Slow-Moving, High-Temperature Applications.



Omega
The Ultimate Lubricant

ITW PPFK reserves the right to modify or change this product for purposes of improving its performance characteristics.
© 2016 ITW PP & F Korea Limited

The Omega Trade Mark is the property of ITW Inc., and is used under licence by ITW PP & F Korea Limited.



The information contained in this publication is to the best of our knowledge and accurate at the time of issue in October, 2016



The Ultimate Lubricant

35

DESCRIPTION:

Omega 35 is a highly-specialized High Temperature Stable grease that has been engineered to continue lubricating applied parts at temperatures where ordinary greases "carbonize" and form abrasives that damage equipment. It consists of a synthetic, non-ash base or "carrier" agent, into which a high concentration of super-micronized, infinitesimal fine-mesh, lubricant-grade Megalite Solid Lubricant (MSL) is suspended.

OPERATING PRINCIPLE:

Omega 35 features a highly unique lubricating principle. Its finely-balanced proportion of synthetic carrier and micronized MSL gives it good penetration power, good "spreadability" and enhanced lubricating qualities.

The synthetic is designed merely to be the "carrier" of the solid lubricant, to enable the latter to be introduced into the part(s) to be lubricated. Once the operating temperature increases to the volatilization range of the synthetic "carrier", it flashes off and leaves the super-fine, Megalite Solid Lubricant (MSL) in place. The MSL remains and continues to provide unparalleled anti-friction lubrication performance to the applied parts.

IN-BUILT SUPERIORITY:

Omega 35's MSL provides many advantages over ordinary high temperature solid lubricants, such as molybdenum disulphide (commonly called "moly"). Moly does have high temperature qualities in the region of 700°C, but at such temperatures oxidize to form hard, abrasive residues that can damage equipment.

PERFECT FOR "SEARING TEMPERATURE" APPLICATIONS:

Omega 35 is engineered as a general-purpose grease for virtually every type of application where exceptionally high heat is unavoidable. Some examples, include:

- OVEN CARS
- BRICK KILN CARS
- STEEL MILLS
- BAKING & COOKING OVENS
- FOUNDRIES...and all slow-moving, high temperature applications.

IMPORTANT:

1. Product should be thoroughly mixed with a paddle to ensure uniform consistency before applying to bearings and other parts to be lubricated.
2. The lubricated parts should be cleaned to remove the previous lubricant completely prior to applying Omega 35.
3. Avoid over-greasing with Omega 35. Otherwise, too much solid lubricant will hinder the free rotation of the bearing. For roller bearings, apply grease to fill about 25% of the housing capacity only. During regular maintenance period, dismantle bearings for cleaning and regreasing.

TYPICAL DATA:

TEST	ASTM TEST METHOD	TEST RESULT
Base Fluid: -		
Viscosity @ 40°C (104°F) cSt	D-445	35
Viscosity @ 100°C (212°F) cSt	D-445	6
Viscosity Index	D-2270	116
Pour Point, °C (°F)	D-97	-8 to -15 (17.6
Flash Point, °C (°F)	D-92	196(385)
4-ball EP weld point, kgf	D-2596	620
4-ball wear scar, mm	D-2266	0.8
Worked Penetration @ 77°F, 150gm. Cone	D-217	270-310
Specific Gravity @ 15°C (60°F)	D-1298	1.33
Dropping Point °C (°F)	D-2265	260(500)+
Texture	--	Smooth
Color	--	Gray/Black
"Megalite" Solid Lubricant Content	--	38 – 42%

The characteristics given above are typical of current production only and slight batch to batch variations should be expected.